

## OUTDOORS

		00100010
Lite	Clear	#1
	Thickness = $1/4$ " = 6 mm	#2 40% White dots
Gap	Air	
	Space = $1/2'' = 12 \text{ mm}$	
Lite	Clear	#3 SunGuard® SuperNeutral 68
	Thickness = $1/4$ " = 6 mm	#4
	Total Unit = .942" = 23.9mm	$Slope = 90^{\circ}$
		INDOORS

	Substrate	Visible Light		Solar Energy		Winter	Summer				
SunGuard®				(Direct)		<b>U-Factor</b>	U-Factor Day time Coef			Relative	
Coating		% Trans-	% Reflectance		% Trans-	Reflect	Night-	Day-time	Coef.	SHGC	Heat
		mittance	Indoor	Outdoor	mittance	% Out	time	Day-time	Coel.		Gain
SN 68 #2	Clear	50	21	21	24	36	.29	.28	.36	.318	77
40%White dots #3	Cical	50	41	41	27	50	.2)	.20	.50	.510	
40% White dots #2	Clear	50	21	21	24	33	.29	.28	.41	.355	85
SN68 #3											

ASHRAE NFRC 2001

The performance values shown above represent NOMINAL VALUES for the center of glass (no spacer or framing). Slight variations may occur due to manufacturing tolerances, point of manufacture, and type of instrumentation used to measure the optical properties.

## **EXPLANATION OF NFRC 2001 STANDARD TERMS**

Visible Light = radiant energy in the wavelength range of 380 nm to 780 nm with Ill. D65 and CIE 2° observer
% Transmittance = percentage of visible light at normal incidence (90° to surface) directly transmitted through the glass
% Reflectance Indoors = percentage of visible light at normal incidence directly reflected from the glass back indoors
% Reflectance Outdoors = percentage of visible light at normal incidence directly reflected from the glass back outdoors
Solar Energy (Direct) = radiant energy from the sun having a wavelength range of 300 nm to 2500 nm at ASTM air mass of 1.5
% Transmittance = percentage of solar energy at normal incidence directly reflected from the glass back outdoors
U-Factor = (also called U-Value) air-to-air thermal conductance of 39" high glazing and associated air films. Units are Btu/hr.ft².F.
Winter-night = 12.3 mph wind at -0.4°F & 69.8°F indoors. Summer = 0 sun, 6.15 mph wind at 89.6°F & 75.2°F still indoor air.
Shading Coef. = (SC) fraction of solar heat, direct (300 to 4500 nm) plus indirect (5 to 40 µm), transferred indoors through the glass. For reference, 1/8" (3.1 mm) clear glass has a value of 1.00 (SC is an older term being replaced by the SHGC).
SHGC = (Solar Heat Gain Coefficient) fraction of solar energy incident on the glazing that is transferred indoors both directly and indirectly through the glazing. The direct gain portion equals the direct solar transmittance, while the indirect is the fraction of the solar energy absorbed to the energy reradiated & convected indoors. No heat gain from warmer outdoor air is included.

 $SHGC = (Direct Solar Trans) + \{[(Indirect Solar Heat Gain) - (Summer U-Value)(89.6°F - 75.2°F)] / (248.209 Btu/hr.ft<sup>2</sup>)\}$  **Relative Heat Gain** (RHG) = total net heat gain to the indoors due to both the air-to-air thermal conductance and the solar heat

gain. The units are Btu/hr.ft<sup>2</sup>. RHG = [(Summer U-Value)(89.6°F - 75.2°F) + (Shading Coef.)(200 Btu/hr.ft<sup>2</sup>)]

This performance analysis is provided under license by Guardian Industries Corp. It is designed to assist the user in evaluating the performance of the glass products identified on this report. Many factors may affect glass performance including glass size, building orientation, shading, wind speed, type of installation, and other factors. While Guardian has made a good faith effort to verify the reliability of this program, it may contain unknown programming errors that could result in incorrect results. With respect to non-Guardian products, this performance analysis may be based on published information from the manufacturer that has not been independently verified by Guardian for accuracy. Moreover, the applicability and results of the analysis are directly related to user inputs and any changes in actual conditions can have a significant affect on the results. GUARDIAN DOES NOT PROVIDE ANY WARRANTY OR GUARANTEE REGARDING THE ACCURACY OF THE INFORMATION IN THIS REPORT OR AGAINST GLASS BREAKAGE OR FOR ANY DIRECT OR INDIRECT DAMAGES THAT MAY BE DUE TO THE USE OF THE PROGRAM.

 $\texttt{SunGuard}^{\scriptscriptstyle (\!\!\!\!)}$  is a registered trademark of Guardian Industries Corp.