## **CENTER OF GLASS U-FACTORS**

PRODUCT	<u>AIR</u>	<u>ARGON</u>
MONOLITHIC GLASS	1.0	N/A
		Γ
INSULATING GLASS		
- UNCOATED	.50	.47
- PILKINGTON ENERGY ADVANTAGE LOW-E	.33	.29
- GUARDIAN SUNGUARD LOW-E #2 (i.e. SN-68, SNX 62/27)	.29	.25
- PILKINGTON ENERGY ADVANTAGE #2 & #4	.25	.22
- GUARDIAN SUNGUARD LOW-E #2 & IS 20 #4	.24	.20
TRIPLE INSULATING GLASS		
- UNCOATED	.30	.27
- PILKINGTON ENERGY ADVANTAGE #2	.25	.22
- GUARDIAN SUNGUARD LOW-E #2 (i.e. SN-68, SNX 62/27)	.21	.19
- GUARDIAN SUNGUARD LOW-E #2 & #5	.16	.12
- GUARDIAN SUNGUARD LOW-E #2, #4 & IS 20 #6	.14	.11