



CENTER OF GLASS U-FACTORS & SHGC VALUES

<u>COG</u> <u>U-FACTOR</u>		<u>SHGC</u>
	HARD COAT LOW-E (2 or 3) - ARGON	
.29	Pilkington Energy Advantage (2) Argon	.63
	Bronze Argon Pilkington Energy Advantage (3)	.45
	Gray Argon Pilkington Energy Advantage (3)	.40
	Green Argon Pilkington Energy Advantage (3)	.44
	Arctic Blue Argon Pilkington Energy Advantage (3)	.34
	Evergreen Argon Pilkington Energy Advantage (3)	.35
	SOFT COAT LOW-E (2 or 3) - AIR	
.29	Guardian SN 68 (2) Air	.38
.28	Guardian SNX 62/27 (2) Air	.27
	SOFT COAT LOW-E (2 or 3) - ARGON	
.25	Guardian SN 68 (2) Argon	.37
	Bronze Argon Guardian SN68 (3)	.31
	Gray Argon Guardian SN68 (3)	.30
	Green Argon Guardian SN68 (3)	.35
.24	Guardian SNX 62/27 (2) Argon	.27
	Bronze Argon Guardian SNX 62/27 (3)	.26
	Gray Argon Guardian SNX 62/27 (3)	.23
	Green Argon Guardian SNX 62/27 (3)	.32
	SOFT COAT LOW-E (2) - AIR - HARD COAT LOW-E (4)	
.24	Guardian SN 68 (2) Air Guardian IS20 (4)	.36
	Bronze Eclipse Advantage (2) Argon Pilkington Energy Advantage (4)	.34
.23	Guardian SN 68 (2) Air Pilkington Energy Advantage (4)	.36
	SOFTCOAT LOW-E (2) - ARGON - HARD COAT LOW-E (4)	
.20	Guardian SN 68 (2) Argon Guardian IS20 (4)	.36
	Guardian SN 68 (2) Argon Pilkington Energy Advantage (4)	.35