

One General Motors Drive
 PO Box 381 - Syracuse, NY 13206
 Phone: 315.437.9971
 Toll Free: 800.962.3211
 Fax: 315.437.8118



www.syracuseglass.com

Our Commitment Shines Through

Flat Glass Products - Tempering
 Insulating - Beveling - Edgework
 All-Glass Doors - Shower Enclosures
 StoreFront and Curtain Wall Systems
 Aluminum Entrances

TEMPERED AND HEAT STRENGTHENED BOW AND WARP TOLERANCES FROM ASTM C1048

EDGE DIMENSIONS	GLASS THICKNESS				
	1/8"	3/16"	1/4"	3/8"	1/2"
0-20"	5/64"	1/8"	5/64"	5/64"	5/64"
>20"-35"	5/64"	5/32"	1/8"	5/64"	5/64"
>35"-47"	5/64"	13/64"	5/32"	5/64"	5/64"
>47"-59"	1/8"	9/32"	13/64"	13/64"	5/64"
>59"-71"	13/64"	11/32"	9/32"	13/64"	5/32"
>71"-83"	15/32"	15/32"	11/32"	15/64"	13/64"
>83"-94"	9/32"	17/32"	15/32"	9/32"	13/64"
>94"-106"		21/32"	17/32"	11/32"	9/32"
>106"-118"		3/4"	21/32"	15/32"	3/8"
>118"-130"			3/4"	9/16"	15/32"
>130"-144"			13/16"	21/32"	17/32"

This chart lists warpage allowed over the entire dimension.
 Localized warp will not exceed 1/16" over any 12" span